

PORON® VXT™ 4701-70-11xxx-120-59T-RR-16.4LF (LR18)



PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density , kg /m ³ (lb. / ft ³)	ASTM D 3574-95, Test A	176 (11)
Tolerance , %		± 10
Thickness , mm (inches)		12.5 & 25 (0.492 & 0.984)
Tolerance , %		6.3 & 8.1
Standard Color (Code)		Pink (120)
Compression Force Deflection , kPa (psi) Typical kPa (psi)	.51 cm/min (0.2" / min). Strain Rate Force Measured @ 25% Deflection	20- 35 (3-5) 28 (4)
Hardness , Durometer, Shore "OO", typical	ASTM D 2240-97	38
Compression Set , % max.	ASTM D 3574-95 Test D @ 70°C (158°F)	10
Resilience by Vertical Rebound , % typical	ASTM D 2632-96	48
Dimensional Stability , % max. change	22 hrs @ 80°C (176°F) in a forced-air oven	± 3
Tensile Strength , kPa (psi), typical	ASTM D 3574-75 Test E	480 (70)
Tensile Elongation , % typical	ASTM D 3574-75 Test E	475
Tear Strength , kN/m (pli), typical	ASTM D 264-91 Die C	3.1 (17.7)
ELECTRICAL AND THERMAL		
Dielectric Strength , kV/m (volts/mil)	ASTM D 149-97a	1100 (28)
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 ⁻⁴ in./in./°C (1.3-1.7 x10 ⁻⁴ in/in/°F)
TEMPERATURE RESISTANCE		
Recommended Constant Use , max.	Rogers Internal Method	90°C (194°F)
Recommended Intermittent Use , max.	Rogers Internal Method	121°C (250°F)
Embrittlement	ASTM D 746-98	-20°C (-4°F)
FLAMMABILITY		
Flammability	UL 94HBF (File E20305) (Pending Certification) CSA Comp HBF (File 188149) (Pending Certification)	Pass Pass
ENVIRONMENTAL		
Water Absorption , Immersion Testing, % weight gain, typical	ASTM D 570-95	23.9

These materials are unsupported and should be processed with the knowledge that stretching of die cut parts can occur when material has not been relaxed.

Notes:

1. All metric conversions are approximate.
2. Additional technical information is available.
3. Typical values should not be used for specification limits.

The information contained in this Data Sheet is intended to assist you in designing with Rogers' PORON Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' PORON Foam Materials for each application. The Rogers logo, Helping power, protect, connect our world, PORON and VXT are trademarks of Rogers Corporation or one of its subsidiaries. © 2016 Rogers Corporation, All rights reserved. Printed in U.S.A. 0616-PDF, Publication # 17-332



The information contained in this Data Sheet is intended to assist you in designing with Rogers' PORON Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' PORON Foam Materials for each application. The Rogers logo, Helping power, protect, connect our world, PORON and VXT are trademarks of Rogers Corporation or one of its subsidiaries. © 2016 Rogers Corporation, All rights reserved. Printed in U.S.A. 0616-PDF, **Publication # 17-332**