

PRODUCT DESCRIPTION

SSP2432 is a sixty five durometer nickel graphite filled conductive adhesive sealant. It will cure within 24 hours but ultimate physical properties could take up to 72 hours to develop. SSP2432 should have excellent adhesion to most substrates.

DATA	Typical Values
Shore A	65
Tensile Strength	250 psi
Specific Gravity	2.2
V.R. Ohm-cm	0.001
Color	Gray

SHELF LIFE

Six months from date of manufacture.

HANDLING & SAFETY

MSDS information is available on request.



**Seal & Design
Able Division**
5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com



**Seal & Design
Corporate Headquarters**
4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com



**Seal & Design
Higbee Division**
6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com

Because we cannot foresee or control varied conditions under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.