

## SSP482-75

### Silicone Shielding Elastomers

#### PRODUCT DESCRIPTION

SSP482-75 is a 75 durometer silicone that is filled with silver plated nickel. This product is supplied as fully cured, conductive sheet stock or ready-to-mold compound. SSP482-75 was designed to meet the requirements outlined in the MIL-G-83528C-Type L specifications.

DATA	Method	Typical Values
Shore A (68- 82 range)	ASTM D2240	75
Tensile psi (200 minimum)	ASTM D412	300 psi
Elongation % (100 min)	ASTM D412	380%
Tear "B" ppi (30 min)	ASTM D624	50
Specific Gravity (3.48 – 4.52)	ASTM D792	4.0
Volume Resistivity ohm - cm (0.005 max)	ASTM D991	.001 oh-cm
Color	-	Tan or Gray
Thermal Stability Range	-	-60°C - 220°C

#### CATALYZING

Raw material available catalyzed and ready for press cure molding. Data above was generated with Varox catalyst system.

#### SHELF LIFE

Uncatalyzed – indefinite, may need freshening after 1-2 years. Catalyzed – 6 months. Cold storage will extend shelf life.

#### HANDLING & SAFETY

MSDS information is available on request.



**Seal & Design  
Able Division**  
5533 Steeles Avenue West Unit 11  
Toronto, Ontario M9L 1S7  
Ph: (416) 741-0750  
Gasket@AbleSealAndDesign.com



**Seal & Design  
Corporate Headquarters**  
4015 Casilio Parkway  
Clarence, NY 14031  
Ph: (716) 759-2222  
Info@SealAndDesign.com  
www.SealAndDesign.com



**Seal & Design  
Higbee Division**  
6741 Thompson Rd N  
Syracuse, NY 13221  
Ph: (315) 432-8021  
Sales@Higbee-Inc.com

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.