

## Material Properties: Simriz® 134 (FFKM)

Original Properties	Simriz 134
Color	Black
Hardness, Shore A, ASTM D2240	90
Tensile Strength, MPa, ASTM D412 Die C	21.5
Tensile Strength, psi, ASTM D412 Die C	3117
Ultimate Elongation, %, ASTM D412 Die C	160
100 % Modulus, MPa, ASTM D412 Die C	16.6
100 % Modulus, psi, ASTM D412 Die C	2407
Temperature Retraction, ASTM D1329	
TR-10, degrees C	-4
Compression Set, ASTM D1414 and ASTM D395 Method B, AS568-214 size O-rings, 70 hours at 200°C	
% Permanent set	25
Compression Set, ASTM D1414 and ASTM D395 Method B, AS568-214 size O-rings, 1,000 hours at 200°C	
% Permanent set	40
Fluid Immersion - Water Bomb, ASTM D471, 70 hrs. at 200°C	
Volume Change, %	+4.5
Steam Immersion - closed vessel, ASTM D471, 1,000 hrs. at 160°C	
Volume Change, %	+3.0
69% Nitric Acid Immersion, ASTM D471, 70 hrs. at 80°C	
Volume Change, %	+7.0
Methyl Ethyl Ketone Immersion, ASTM D471, 70 hrs. at 80°C	
Volume Change, %	+3.1
Cyclohexyl Amine Immersion, ASTM D471, 70 hrs. at 40°C	
Volume Change, %	+1.5

Compatible with:

Aliphatic and aromatic hydrocarbons, Ketones and esters, Strong acids and bases, Strong amines and corrosion inhibitors



**Seal & Design**  
**Able Division**

5533 Steeles Avenue West Unit 11  
 Toronto, Ontario M9L 1S7  
 Ph: (416) 741-0750  
 Gasket@AbleSealAndDesign.com



**Seal & Design**  
**Corporate Headquarters**

4015 Casilio Parkway  
 Clarence, NY 14031  
 Ph: (716) 759-2222  
 Info@SealAndDesign.com  
 www.SealAndDesign.com



**Seal & Design**  
**Higbee Division**

6741 Thompson Rd N  
 Syracuse, NY 13221  
 Ph: (315) 432-8021  
 Sales@Higbee-Inc.com