



DATA SHEET

ePTFE Membrane Laminate

Product Type: QL209

Description: Hydrophobic ePTFE Membrane Laminate
Functional Layer: PTFE
Backer Material: Polypropylene

Reference Pore Size	Nom. 0.45um
Water Entry Pressure	Nom. >21 psi (1.4 bar) avg., ASTM D751
Air Permeability	Nom. 0.6-1.2 ft ³ /ft ² /min @ 125 Pa (60 - 120 l/cm ² /h @ 0.07 bar), ASTM D737
Thickness	Nom. 6-10 mil (0.15 - 0.25 mm), ASTM D1777
IPA Bubble Point	Nom. >11 psi (0.75 bar) avg., ASTM F316
Available Dimensions	OEM membranes as custom slit roll goods. Membrane vents in customized shapes.

All above data is nominal and provided for information only and is subject to change. All metric conversions are approximate.

**Seal & Design
Able Division**

5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com

**Seal & Design
Corporate Headquarters**

4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com

**Seal & Design
Higbee Division**

6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com