

**BISCO® MF1® Industrial Grade Foam
Bun Cellular Silicone Foam – Data Sheet**

PROPERTY	TEST METHOD	MF1-35 (Soft)	MF1-55 (Medium)	MF1-75 (Firm)
Standard Color		White	White or Gray	White
Density, kg/m ³ (pcf)	ASTM D 1056	6.5 (104)	7.0 (112)	8.0 (128)
Compression Force Deflection, kPa (psi)	ASTM D 1056	----	2.8 – 10.3 (0.4 – 1.5)	----
Compression Set, % (22 hours, 50% compressed, 100°C)	ASTM D 1056	1.5%	1.5%	1.5%
Tensile Strength, kPa (psi)	ASTM D 412	86 (12.5)	86 (12.5)	93 (13.5)
Elongation, %	ASTM D 412	45	45	35
Water Absorption, %	ASTM D570	< 5.0	< 5.0	< 5.0
Flame resistance	FVMSS302 – self extinguishing	N/A	Pass	N/A
THERMAL PROPERTIES				
Thermal Conductivity (W/m*K)	ASTM C518		0.044	
Low Temperature Flex -67°F (-55°C)	ASTM D 1056	Pass	Pass	Pass
Recommended Constant Use, Max °C (°F)		200 (392)	200 (392)	200 (392)
Recommended Intermittent Use, Max °C		250 (482)	250 (482)	250 (482)
CERTIFICATIONS				
UL Certification	UL94 V-0 and HF-1	N/A	Gray Only ¹	N/A

- ¹ UL94 V-0 and HF-1 - Gray color only, minimum thickness 0.094"
- All metric conversions are approximate
- Additional technical information is available
- Typical values should not be used for specification limits
- ---- Indicates no testing performed

The information contained in this Data sheet is intended to assist you in designing with Rogers' BISCO Silicone foam materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' BISCO Silicone foam materials for each application. The Rogers logo, Helping Power, protect, connect our world, BISCO and MF1 are trademarks of Rogers Corporation or one of its subsidiaries. ©2016 Rogers Corporation, All rights reserved. Printed in U.S.A. 0716-PDF.

Publication #180-320

Helping **power, protect, connect** our world[®]



**Seal & Design
Able Division**
5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com



**Seal & Design
Corporate Headquarters**
4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com



**Seal & Design
Higbee Division**
6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com