

BISCO® Silicones

BISCO® RS-720

Continuous Roll Closed-Cell Silicone Sponge – Data Sheet

¹Typical values are a representation of an average property value of a given population. All metric conversions are approximate. Typical properties are based on 6.35mm (0.250") sample. For specification values, please contact Rogers Corporation.

PROPERTY	TEST METHOD	TYPICAL PROPERTIES	
Density, kg / m ³ (lb. / ft ³)	ASTM D 3574	280 (17.5)	
Thickness, mm (in)		2.4 (0.094)	3.2-12.7 (0.125 – 0.500)
Compression Force Deflection Specification Range, kPa (psi)	ASTM D 1056	34.5-82.7 (5 - 12)	31-62 (4.5 - 9)
Compression Set, %	ASTM D 1056 22 hours @ 100°C, 50% compressed, 24 hours recovery	<15	
Tensile Strength, MPa (psi)	ASTM D 412	0.52 (75)	
Elongation to Failure, %	ASTM D 412	175	
Water Absorption, %	ASTM D 1056	<3	
Water Sealing Properties	Water pressure: 10.3 kPa (1.5 psi) Gasket width: 6.34 mm (0.250") Compression: 30% Gasket thickness: 3.175 mm (0.125")	No Leakage	
Standard Color		Fog Gray	
TEMPERATURE RESISTANCE			
Recommended Constant Use, Max °C (Max °F)		205°C (401°F)	
Recommended Intermittent Use, Max °C (Max °F)		260°C (500°F)	
Low Temperature Brittleness, °C (°F)	ASTM D 746	-55°C (-67°F)	
Thermal Conductivity, w/m K (BTU in hr/ft ² /F)	ASTM C 518	0.07 (0.48)	
FLAMMABILITY			
Flame Resistance, pass >= mm (inch)	FMVSS 302	2.4 (0.094)	
CERTIFICATIONS			
UL Certification	Gaskets & Seals JMLU2	UL50, UL50E, UL508 & UL157	
TOLERANCE, mm (in)			
2.4-6.35 (0.094-0.250)		±0.51 (±0.020)	
9.53 (0.375)		±1.14 (±0.045)	
12.70 (0.500)		±1.49 (±0.059)	

The information contained in this Data sheet is intended to assist you in designing with Rogers' BISCO Silicone foam materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' BISCO Silicone foam materials for each application. The Rogers logo, Helping Power, protect, connect our world and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. ©2016 Rogers Corporation, All rights reserved. Printed in U.S.A. 0216-PDF. Publication #180-310



**Seal & Design
Able Division**
5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com

**Seal & Design
Corporate Headquarters**
4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com

**Seal & Design
Higbee Division**
6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com