



SUBMITTAL SHEET (effective 06/08/07)

AG1 Continuous Rolls/Sheets

Physical Properties

Polymer			PVC/NBR/CR
Color			Black
Classifications			
ASTM D 1056-68			SCE41
ASTM D 1056-00			2C1
Suffix Requirements			C1, F1, M
1. 25% Compression Resistance (psi)	ASTM D 1056		2.0 – 5.0
2. 50% Compression Set (%)	ASTM D 1056		40 max.
3. Density (lb/ft ³)	ASTM D 1056		3.5 to 5.0
4. Water Absorption (lb/ft ²)	ASTM D 1667		0.1 max.
5. Tensile (psi)	ASTM D 412		50 min.
6. Elongation (%)	ASTM D-412		100 min.
7. Flammability (1)			
FMVSS302	0 Burn Rate		Pass
8. Temperature Use (2)	ASTM D-1056	Cold Crack	-40
		High (3)	200
Standard Roll Widths (in)			54" or 60"
Maximum Gauge (in)			1-1/4"

(1) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

(2) This recommendation is based on polymer type only. For specific application requirements please contact technical service dept.

(3) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service department.

Note: Available in Colors

Skin 2 sides 1/8" – 1"

PVC = Polyvinyl Chloride

NBR = Acrylonitrile Butadiene Rubber

CR = Chloroprene (Neoprene®)

Minimum gauge for skin two sided products is 3/4"

Other gauges and widths may be available. Please contact Customer Service.

**Seal & Design
Able Division**

5533 Steeles Avenue West Unit 11
Toronto, Ontario M9L 1S7
Ph: (416) 741-0750
Gasket@AbleSealAndDesign.com

**Seal & Design
Corporate Headquarters**

4015 Casilio Parkway
Clarence, NY 14031
Ph: (716) 759-2222
Info@SealAndDesign.com
www.SealAndDesign.com

**Seal & Design
Higbee Division**

6741 Thompson Rd N
Syracuse, NY 13221
Ph: (315) 432-8021
Sales@Higbee-Inc.com