



## Garlock FAWN GYLON® 3500

### MATERIAL PROPERTIES\*:

<b>Color:</b>	Fawn
<b>Composition:</b>	PTFE with silica
<b>Fluid Services<sup>1</sup>:</b>	Strong acids (except hydrofluoric), steam, solvents, hydrocarbons, chlorine and cryogenics
<b>Temperature<sup>2</sup>, °F (°C)</b>	
Minimum:	-450 (-268)
Continuous Max:	+500 (+260)
<b>Pressure<sup>2</sup>, Maximum, psig (bar):</b>	1200 (83)
<b>P x T (max.)<sup>2</sup>, psig x °F (bar x °C):</b>	
1/32 and 1/16":	350,000 (12,000)
1/8"	250,000 (8,600)
<b>Flammability:</b>	Will Not Burn
<b>Bacterial Growth:</b>	Will Not Support
<b>Meets Specification:</b>	ABS (American Bureau of Shipping), FDA (Food and Drug Administration) and USDA (US Department of Agriculture)

### TYPICAL PHYSICAL PROPERTIES\*:

<b>ASTM F36</b>	<b>Compressibility, %:</b>	7-12		
<b>ASTM F36</b>	<b>Recovery, %:</b>	40		
<b>ASTM F38</b>	<b>Creep Relaxation, %:</b>	18		
<b>ASTM D1708</b>	<b>Tensile, Across Grain, psi (N/mm<sup>2</sup>):</b>	2000 (13.8)		
<b>ASTM D792</b>	<b>Specific Gravity:</b>	2.10		
<b>ASTM D1708</b>	<b>Modulus @ 100% Elongation, psi (N/mm<sup>2</sup>):</b>	1600 (11.0)		
<b>ASTM F433</b>	<b>Thermal Conductivity (K) W/m<sup>2</sup>K (Btu·in./hr·ft<sup>2</sup>·°F)</b>	0.36-0.45 (2.50-3.15)		
<b>ASTM D149</b>	<b>Dielectric Properties, range, volts/mil.</b>			
	Sample conditioning	<u>1/16"</u>	<u>1/8"</u>	
	3 hours at 250°F:	362	-	
	96 hours at 100% Relative Humidity:	61	-	
<b>ASTM F586</b>	<b>Design Factors</b>	<u>1/16" &amp; Under</u>	<u>1/8"</u>	
	"m" factor:	5.0	5	
	"y" factor, psi (N/mm <sup>2</sup> )	2750 (19.0)	3500 (24.1)	
<b>ROTT</b>	<b>Gasket Constants, 1/16"</b>	Gb=949	a=0.253	Gs=2.6
	1/8"	Gb=1980	a=0.169	Gs=0.393

## SEALING CHARACTERISTICS\*

	ASTM F37B Fuel A	DIN 3535-4 Gas Permeability
<b>Gasket Load</b> , psi (N/mm <sup>2</sup> ):	1000 (7)	4640 (32)
<b>Internal Pressure</b> , psig (bar):	9.8 (0.7)	580 (40)
<b>Leakage</b>	<b>0.22 ml/hr.</b>	<b>&lt;0.015 cc/min</b>

### Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

\* Values do not constitute specification Limits

<sup>1</sup> See Garlock chemical resistance guide.

<sup>2</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum P<sub>xT</sub>, consult Garlock Applications Engineering.